



TYGLU™



Wood Floor Bonding Agent

This revolutionary bonding agent can be used to ensure adhesion for many types of wood sports floors and commercial wood floors. The product acts as an intermediate bonding layer between the existing floor (water-based or oil-modified coating) and the new topcoat water-based coating. Using this system eliminates all dust, mess and equipment associated with screening wood floors. This is the only product which is tried and proven for wood coating adhesion without the use of aggressive sanding screens.

Uses

- Sports floors – Gymnasiums, aerobic and exercise floors
- Commercial – Offices, assembly halls, retail, classrooms

Benefits

- Dustless recoating system
- No special equipment required
- Simplest wood recoating system
- Quick and easy training
- Saves time, labor and materials
- One top coat procedure
- Low odor

Note - Do not use over any paste wax surfaces. If unsure, always prepare a test patch to determine potential adhesion. TyGlu™ is recommended for recoat applications only.

Properties

Color (dried).....	Clear
Coverage.....	2500 sq. ft./gal.
Dry time.....	1 hour
Recoat time.....	6 hours
Flash Point	Greater than 200° F
Freeze/thaw stability3 cycles
Viscosity	4.0 - 6.5 centipoise
Weight per gallon.....	8.45 lbs.
VOC	<125 g/L
Shelf life.....	1 year

Directions For Use

Read the entire label before using this product.

For use on gymnasium and other wood floors. Clean floor with PK Cleaner and blue pads according to label instructions. Multiple cleanings may be necessary. Be sure floor is entirely free of dirt, oil, and other residue. Rinse the floor by damp mopping with clean water or an auto scrubber until the rinse water remains clear after use. Allow floor to dry completely before applying TyGlu. Box fans may be used to speed up the drying process. Shake or mix container before opening. Apply a small amount of TyGlu to an area of the floor and use sponge mop to spread it in a thin, uniform layer. For large floors, pour TyGlu into a clean, dry mop bucket. Soak a new, lint-free rayon mop in TyGlu and wring out. Work around the floor until all areas have been coated. Be sure that every area of the floor intended for recoat is coated with TyGlu. Any missed spots may result in poor adhesion to topcoat. The floor should have a wet appearance but there should be no puddles. Allow to dry approximately one hour with good ventilation and air movement across the floor. If there are areas where the TyGlu has not dried, wipe the area with a clean, water-dampened rag. Do not exceed six hours before applying the topcoat or TyGlu may lose effectiveness. If the six-hour window is surpassed, tack the floor with GT Cleaner to remove any airborne dust before reapplying TyGlu. Apply the Betco water-based topcoat of your choice according to label instructions. Refer to the Water-Based Wood Coatings Application & Procedure Guide for detailed instructions.

Safety

Keep out of reach of children. For industrial and commercial use. **CAUTION:** May cause skin and eye irritation. Avoid contact with eyes, skin, and clothing. Wash thoroughly after handling. Use only with adequate ventilation. **FIRST AID:** IF ON SKIN OR IN EYES: Flush with large quantities of water. IF INHALED: Remove to fresh air. IF SWALLOWED: Contact a poison control center or doctor for treatment advice. Do NOT induce vomiting unless instructed to do so by physician. SEE MATERIAL SAFETY DATA SHEET.

Available In

Case/4 - 1 Gallon (3.78 L): Item #69104-00
Box/2-1.125 Gallon Bags (4.25 L): Item #69159-00 (QUICKCOAT®)

Literature Item #69192-92

